



DEQING SINO PIGMENTS CO.,LTD

ORGANIC PIGMENT

HIGH PERFORMANCE ORGANIC PIGMENT



SINOPIGMENT
信诺颜料

DEQING SINOPIGMENTS CO.,LTD.

Add: DEQING ECONOMIC AND DEVELOPMENT ZONE WUKANG 313200
DEQING ZHEJIANG PROVINCE CHINA

Tel: +86-572-8322686, 8820387, 8322666 **Fax:** +86-572-8820368
Email: trustpigment@yahoo.com.cn **Website:** //www.sinopigments.com.

WWW.SINOPIGMENTS.COM

All for your colorful life!

DEQING SINO PIGMENTS CO.,LTD

About Us

Deqing Sino Pigments Co., Ltd is a joint venture, established in 1990, which specializes in producing, processing and developing organic pigments, chrome yellow pigment and other pigments. Our product range includes Red, Yellow, Orange, Violet, Blue and green, with 8000mt capacity of organic pigment, and 5000mt capacity of chrome yellow.

Our products are excellent in using in paints, inks, coating, leather, plastic, compound material, etc. And all of our products were produced following the ISO 9001, REACH. Guaranteeing high products quality and competitive prices, we have established good business relationship with clients from Southeast Asia, Middle East, Europe, Africa, North America, South America and so on. We have finished pre-registration due to Reach requirement.

Our company has advanced pigment testing equipment and strict management mode to ensure the stability of quality. We concern about the actual needs of customers, and insist on developing the unique properties of organic pigments. Furthermore, we subdivide products and enhance additional functions of applications in different areas.

Our company has been committed to improving the quality, stability control, communication and coordination with customers, environmental protection, create top-grade famous brand of pigments. Welcome every customer to work together with us to create colorful and beautiful homeland.



SINOPIGMENT
信诺颜料



All for your
colorful life!

SINOPIGMENT



DEQING SINO PIGMENTS CO.,LTD

Add: DEQING ECONOMIC AND DEVELOPMENT ZONE WUKANG 313200
DEQING ZHEJIANG PROVINCE CHINA
Tel: +86-572-8322686. 8820387. 8322666 Fax: +86-572-8820368
Email: trustpigment@yahoo.com.cn

Organic Pigment mainly used in water based ink.

Color	Product Name	Color Index	Physical and Chemical Property								
			Heat Resistance °C	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Alcohol Resistance	Benzene Resistance	Ester Resistance
Yellow	Fast Yellow 10G-W	PY.3	160	5	5	5	4	4	4	4	4
	Benzidine Yellow GW	PY.12	180	5	5	5	4-5	5	4	4	4
	Permanent Yellow GR	PY.13	180	5	5	5	5	5	4	4	4
	Permanent Yellow G	PY.14	200	6	5	5	5	4	5	4	4
	Permanent Yellow 5GX	PY.74	160	7	5	5	5	4	4	3	3
	Permanent Yellow 5GX	PY.83	200	7	5	5	5	5	4	4	3
Red	Permanent Red 2R	PR.2	140	7	3	4	5	4	4	5	3
	Permanent Red 2RY	PR.2	85	7	3	4	5	4	4	5	3
	Vermilion R	PR.4	120	6	5	5	5	4	3	4	4
	Permanent Red F4R	PR.8	120	6	4	5	5	5	4	4	4
	3132 Scarlet Red	PR.21	120	6	5	5	4	3	4	3	3
	Brilliant Red GY	PR.22	140	6	3	5	4	2	3	3	3
	Permanent Red BBN	PR.48:1	180	6	4	5	5	4	4	5	5
	Permanent Red BBC	PR.48:2	200	6	5	5	5	5	4	5	5
	Permanent Red BBS	PR.48:3	180	6	5	5	4	5	5	5	5
	Lake Red CW	PR.53:1	170	4	4	4	4	4	3	4	4
	Lithol Red R-W	PR.49:1	130	8	4	5	4	4	4	5	5
	Lithol Red RB-W	PR.49:2	160	5	4	4	4	4	4	4	4
	Lithol Red RB-W	PR.57:1	180	8	4	4	4	4	3	4	4
	Fast Pink Toner W	PR.81	120	4	5	5	4	4	5	5	5
	Permanent Red FGR	PR.112	170	7	5	5	5	4	4	5	5
	Permanent Pink FBB	PR.146	120	5	4	5	4	4	4	4	4
	Permanent Red F5RK	PR.170	180	7	5	5	4	5	4	4	4
	Permanent Red F3RK	PR.170	180	8	5	5	4	4	4	5	5
	Permanent Red F7RK	PR.266	180	7	5	5	4	5	4	5	4
	Permanent Red F6B	PR.184	180	7	5	5	5	5	5	4	4
	Permanent Red 8A	PR.268	180	7	5	4	4	4	4	4	4
	Permanent Red 6A	PR.269	180	7	5	4	4	4	4	4	4
Orange	Permanent Orange RN	PO.5	130	4	4	4	4	4	4	4	4
	Permanent Orange G	PO.13	150	7	3	4	4	4	3	3	3
	Permanent Orange GRN	PO.16	180	6	5	5	5	5	5	4	4
	Permanent Orange F2L	PO.34	180	6	4	5	4	5	4	5	4
Violet	Fast Violet Toner W	PV.3	120	5	5	5	5	5	5	4	4
Blue	Fast Blue Toner BO	PB.1	140	4	3	4	4	4	4	4	4
	Fast Blue Toner 2R	PB.10	180	5	3	4	4	3	4	4	4
	Fast Blue Toner RM	PB.14	140	4	3	4	4	3	4	4	4

The above information is just for your reference. Please do the testing before using it.

Organic Pigment mainly used in water based ink.

Color	Product Name	Color Index	Physical and Chemical Property								
			Heat Resistance °C	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Alcohol Resistance	Benzene Resistance	Ester Resistance
Blue	Fast Blue Toner CF	PB.62	140	3	3	4	4	3	4	4	4
	Phthalocyanine Blue B-W	PB.15:0	200	8	5	5	5	5	5	5	4
	Phthalocyanine Blue BGS-W	PB.15:3	200	8	5	5	5	5	5	5	4
Green	Phthalocyanine Green GW	PG.7	200	8	5	5	5	5	5	5	5

Organic Pigment mainly used in solvent based ink

Color	Product Name	Color Index	Physical and Chemical Property								
			Heat Resistance °C	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Alcohol Resistance	Benzene Resistance	Ester Resistance
Yellow	Benzidine Yellow GN	PY.12	180	5	5	5	5	5	5	5	5
	Permanent Yellow BRL	PY.13	180	5	5	5	5	4	4	4	4
	Permanent Yellow B3L	PY.13	180	5	5	5	5	4	4	4	4
	Permanent Yellow GTL	PY.14	200	6	5	5	5	4	5	4	4
	Permanent Yellow 5GXS	PY.74	160	7	5	5	5	4	4	3	3
	Permanent Yellow HRT	PY.83	200	7	5	5	5	5	4	4	3
Red	Permanent Red BBL	PR.48:2	200	6	5	5	5	5	4	5	5
	Lake Red CNL	PR.53:1	160	4	4	4	4	4	3	4	4
	Lake Red CNLB	PR.53:1	160	4	4	4	4	4	3	4	4
	Lithol Rubine 4BL	PR.57:1	160	5	4	4	4	4	4	4	4
	Lithol Rubine 4BGL	PR.57:1	160	5	4	4	4	4	4	4	4
	Permanent Red F7RK	PR.266	180	7	5	5	4	5	4	5	4
	Fast Pink Toner S	PR.81	120	4	5	5	4	4	5	5	5
	Permanent Orange G	PO.13	150	7	3	4	4	4	3	3	3
Violet	Permanent Orange F2L	PO.34	180	6	4	5	4	5	4	5	4
	Fast Violet Toner S	PV.3	120	5	5	5	5	5	5	4	4
Blue	Phthalocyanine Blue BGF5	PB.15:4	200	7	5	5	5	5	5	5	4
Green	Phthalocyanine Green GS	PG.7	200	8	5	5	5	5	5	5	5

The above information is just for your reference. Please do the testing before using it.



All for your
colorful life!

DEQING SINO PIGMENTS CO.,LTD

Add: DEQING ECONOMIC AND DEVELOPMENT ZONE WUKANG 3 13200
DEQING ZHEJIANG PROVINCE CHINA
Tel: +86-572-8322686. 8820387. 8322666 Fax: +86-572-8820368
Email: trustpigment@yahoo.com.cn

Organic Pigment mainly used in offset ink.

Color	Product Name	Color Index	Physical and Chemical Property								
			Heat Resistance °C	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Alcohol Resistance	Benzene Resistance	Ester Resistance
Yellow	Benzidine Yellow GTR	PY.12	180	5	5	5	4-5	5	4	4	4
	Benzidine Yellow HF	PY.12	180	5	5	5	4-5	5	4	4	4
	Permanent Yellow GR-F	PY.13	180	5	5	5	5	4	4	4	4
	Permanent Yellow 2GS	PY.14	200	6	5	5	5	4	5	4	4
	Permanent Yellow LBE	PY.174	180	7	5	5	5	4	4	4	5
	Permanent Yellow LBS	PY.174	180	7	5	5	5	4	4	4	5
	Permanent Yellow GRX	PY.176	200	6	5	5	5	4	4	4	3
	Permanent Yellow LBF	PY.188	180	4	5	5	5	5	4	4	4
Red	Permanent Red BBN	PR.48:1	180	6	4	5	5	4	4	5	5
	Permanent Red BBC	PR.48:2	200	6	5	5	5	5	4	5	5
	Lake Red C	PR.53:1	170	4	4	4	4	4	3	4	4
	Lake Red CS	PR.53:1	170	4	4	4	4	4	3	4	4
	Lake Red CNL	PR.53:1	170	4	4	4	4	4	3	4	4
	Lithol Red R	PR.49:1	130	8	4	5	4	4	4	5	5
	Lithol Rubine 4BN	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine 4BH	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine 8BN	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine 4BE	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine 4BD	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine 4BC	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine SMA	PR.57:1	180	8	4	4	4	4	3	4	4
	Lithol Rubine SMB	PR.57:1	180	8	4	4	4	4	3	4	4
	Fast Pink Toner	PR.81	120	4	5	5	4	4	5	5	5
	Permanent Pink FBB	PR.146	120	5	4	5	4	4	4	4	4
	Permanent Red F3RK	PR.170	180	8	5	5	4	4	4	5	5
	Permanent Red F7RK	PR.266	180	7	5	5	4	5	4	5	4
	Permanent Red F6B	PR.184	180	7	5	5	5	5	5	4	4
	Permanent Red 2A	PR.210	180	7	5	5	4	4	4	4	4
	Permanent Red 8A	PR.268	180	7	5	4	4	4	4	4	4
Orange	Permanent Red 6A	PR.269	180	7	5	4	4	4	4	4	4
	Permanent Orange G	PO.13	150	7	3	4	4	4	3	3	3
	Permanent Orange GRN	PO.16	180	6	5	5	5	5	5	4	4
Violet	Permanent Orange F2L	PO.34	180	6	4	5	4	5	4	5	4
	Fast Violet Toner	PV.3	120	5	5	5	5	5	5	4	4
	Fast Blue Toner BO	PB.1	140	4	3	4	4	4	4	4	4
Blue	Fast Blue Toner 2R	PB.10	180	5	3	4	4	3	4	4	4
	Fast Blue Toner RM	PB.14	140	4	3	4	4	3	4	4	4
	Phthalocyanine Blue B-O	PB.15:0	200	8	5	5	5	5	5	5	4
	Phthalocyanine Blue BGS-O	PB.15:3	200	8	5	5	5	5	5	5	4
Green	Phthalocyanine Green GO	PG.7	200	8	5	5	5	5	5	5	5

Organic Pigment mainly used in plastic.

Color	Product Name	Color Index	Physical and Chemical Property						
			Heat Resistance °C	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Immigration
Yellow	Benzidine Yellow G	P.Y.12	180	5	5	5	4-5	5	4
	Permanent Yellow GR	P.Y.13	180	5	5	5	5	4	4
	Permanent Yellow G	P.Y.14	200	6	5	5	5	4	5
	Permanent Yellow 2G	P.Y.17	180	6	5	5	5	4	4
	Permanent Yellow TRP	P.Y.62	200	7	5	5	5	4	4
	Permanent Yellow F10G	P.Y.81	200	7	5	5	5	4	4
	Permanent Yellow HR	P.Y.83	200	7	5	5	5	5	4
	Permaent Yellow GRP	P.Y.168	260	7	5	5	5	4	5
	Fast scarlet BR	P.R.38	200	7	3	4	5	4	4
Red	Permanent Red BBN	P.R.48:1	180	6	4	5	5	4	4
	Permanent Red BBC	P.R.48:2	200	6	5	5	5	5	4
	Permanent Red 2BP	P.R.48:2	200	6	5	5	5	5	5
	Permanent Red 2BSP	P.R.48:3	180	6	5	5	4	5	5
	Permanent Red BBM	P.R.48:4	180	7	3	4	4	5	4
	Lake Red CP	P.R.53:1	170	4	4	4	4	4	4
	Lithol Rubine 4BP	P.R.57:1	180	8	4	4	4	4	4
	Lithol Bordeaux 2R	P.R.63:1	160	6	4	5	5	4	4
	Permanent Pink FBB	P.R. 146	120	5	4	5	4	4	4
	Permanent Red F5RK	P.R.170	180	7	5	5	4	5	5
	Permanent Red F3RK	P.R.170	180	8	5	5	4	4	5
	Permanent Red F7RK	P.R.266	180	7	5	5	4	5	5
Orange	Permanent Orange RN	P.O.5	130	4	4	4	4	4	4
	Permanent Orange G	P.O.13	150	7	3	4	4	4	4
	Permanent Orange GRN	P.O.16	180	6	5	5	5	5	4
Blue	Permanent Orange F2L	P.O.34	180	6	4	5	4	5	4
	Fast Blue Toner BO	P.B.1	140	4	3	4	4	4	4
	Phthalocyanine Blue BP	P.B.15:0	200	8	5	5	5	5	5
	Phthalocyanine Blue BSP	P.B.15:1	200	8	5	5	5	5	5
Green	Phthalocyanine Blue BGS-P	P.B.15:3	200	8	5	5	5	5	5
	Phthalocyanine Green GP	P.G. 7	200	8	5	5	5	5	5



All for your
colorful life!



DEQING SINO PIGMENTS CO.,LTD

Add: DEQING ECONOMIC AND DEVELOPMENT ZONE WUKANG 3 13200
DEQING ZHEJIANG PROVINCE CHINA
Tel: +86-572-8322686. 8820387. 8322666 Fax: +86-572-8820368
Email: trustpigment@yahoo.com.cn

Organic pigment mainly used in paint & coating

Color	Product Name	Color Index	Physical and Chemical Property						Applications			
			Heat Resistance℃	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Solvent Base	Water Base	Industrial	Textile printing
Yellow	Permanent Orange RN	P.Y.1	160	5	5	5	4	4		●	●	●
	Fast Yellow 10G-	P.Y.3	160	5	5	5	4	4		●	●	●
	Benzidine Yellow G	P.Y.12	180	5	5	5	4-5	5				●
	Permanent Yellow GR	P.Y.13	180	5	5	5	5	4				●
	Permanent Yellow G	P.Y.14	200	6	5	5	5	4				●
	Permanent Yellow RN	P.Y.65	6	180	5	5	5	4			●	●
	Permanent Yellow 5GX	P.Y.74	160	7	5	5	5	4		●	●	
	Permanent Yellow 5GO	P.Y.74	160	7	5	5	5	4			△	
	Permanent Yellow F10G	P.Y.81	200	7	5	5	5	4				●
	Permanent Yellow HR	P.Y.83	200	7	5	5	5	5			●	△
	Permanent Yellow HRZ	P.Y.83	200	7	5	5	5	5			△	
	Permanent Yellow FGL	P.Y.97	200	7	5	5	5	4			△	
	Permanent Yellow 4G	P.Y.151										
Red	Permanent Red F2R	P.R.2	140	7	3	4	5	4	●	●	●	●
	Toluidine Red	P.R.3	85	7	3	4	5	4	●	●	●	
	Permanent Red F4R	P.R.8	120	6	4	5	5	5			●	●
	Toluidine Maroon	P.R.13	140	6	4	4	4	4			●	
	3132 Scarlet Red	P.R.21	120	6	5	5	4	3	●	●	●	
	Brilliant Red GY	P.R.22	120	6	3	5	4	2				●
	Fast Rose Red	P.R.23	140	6	4	4	4	4				●
	Rubine Bordeaux before	P.R.31	160	7	5	5	4	5		●		●
	Permanent Red BBC	P.R.48:2	200	6	5	5	5	5			●	
	Permanent Red 2BP	P.R.48:2	200	6	5	5	5	5				
	Permanent Red BBS	P.R.48:3	180	6	5	5	4	5			●	
	Permanent Red 2BSP	P.R.48:3	200	6	5	5	4	5				
	Permanent Red BBM	P.R.48:4	180	7	3	4	4	5	●	●	●	
	Lithol Red R-	P.R.49:1	130	8	4	5	4	4		●	●	●

Organic pigment mainly used in paint & coating

Color	Product Name	Color Index	Physical and Chemical Property						Applications			
			Heat Resistance℃	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Solvent Base	Water Base	Industrial	Textile printing
Red	Lithol Scarlet S6B	P.R.52:1	180	6	4	4	4	4			●	
	Lake Red CW	P.R.52:1	170	4	4	4	4	4				
	Lithol Rubine A6B	P.R.57:1	180	8	4	4	4	4				
	Lithol Rubine 4BP	P.R.57:1	250	8	4	4	4	4				
	Lithol Bordeaux 2R	P.R.63:1									●	
	Permanent Red FGR	P.R.112	170	7	5	5	5	4	●	●	●	●
	Permanent Pink FBB	P.R.146	120	5	4	5	4	4		●	●	●
	Permanent Red F5RK	P.R.170	180	7	5	5	4	5			●	●
	Permanent Red F3RK	P.R.170	180	8	5	5	4	4	●	●	●	
	Permanent Red F7RK	P.R.266	180	7	5	5	4	5			●	●
	Permanent Red F6B	P.R.184	180	7	5	5	5	5	●	●	●	●
	Permanent Red 2A	P.R.210	180	7	5	5	4	4	●	●		●
	Permanent Red 8A	P.R.268	180	7	5	4	4	4	●	●		●
	Permanent Red 6A	P.R.269	180	7	5	4	4	4	●	●		●
Orange	Permanent Orange RN	P.O.5	130	4	4	4	4	4	●	●	●	●
	Permanent Orange G	P.O.13	150	7	3	4	4	4			●	●
	Permanent Orange GRN	P.O.16	180	6	5	5	5	5	●			
	Permanent Orange F2L	P.O.34	180	6	4	5	4	5	●	●	△	●
Violet	Fast Violet Toner	P.V.3	120	5	5	5	5	5		●		●
Blue	Fast Blue Toner BO	P.B.1	140	4	3	4	4	4	●	●		●
	Fast Blue Toner 2R	P.B.10	180	5	3	4	5	3		●		●
	Fast Blue Toner RM	P.B.14	140	4	3	5	5	3		●		●
	Phthalocyanine Blue B	P.B.15:0	200	8	5	5	5	5	●	●	●	●
	Phthalocyanine Blue BS	P.B.15:1	200	8	5	5	5	5	●	●	●	
	Phthalocyanine Blue BGS	P.B.15:3	200	8	5	5	5	5	●	●	●	●
Green	Phthalocyanine Green G	P.G.7	200	8	5	5	5	5	●	●	●	●

△:recommended ● can be sued



All for your
colorful life!

DEQING SINO PIGMENTS CO.,LTD

Add: DEQING ECONOMIC AND DEVELOPMENT ZONE WUKANG 3 13200
DEQING ZHEJIANG PROVINCE CHINA
Tel: +86-572-8322686. 8820387. 8322666 Fax: +86-572-8820368
Email: trustpigment@yahoo.com.cn

High Performance Organic Pigment

Color	Item	C. I.No.	Physical and Chemical Property							Applications		
			Heat Resistance℃	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Immigration	Ink	Paint	Plastic
Yellow	Pigment Yellow 110	P.Y.110	300	8	5	5	5	5	5		△	△
	Pigment Yellow 138	P.Y.138	300	8	5	5	5	5	5		△	△
	Permanent Yellow 2R	P.Y.139	280	8	5	5	5	5	5			△
	Permanent Yellow 3R	P.Y.139	280	8	5	5	5	5	5		△	
	Permanent Yellow 4G	P.Y.150	250	8	5	5	5	5	5		△	
	Permanent Yellow 5GN	P.Y.150	250	8	5	5	5	5	5			△
	Permanent Yellow H4G	P.Y.151	250	8	5	5	5	5	5	△	△	△
	Permanent Yellow H3G	P.Y.154	250	8	5	5	5	5	5	△	△	△
	Permanent Yellow 3GP	P.Y.155	250	8	5	5	5	5	5		△	△
	Permanent Yellow HG	P.Y.180	280	8	5	5	5	5	5	△	△	△
	Permanent Yellow H3R	P.Y.181	250	8	5	5	5	5	5	△	△	△
	Pigment Yellow 3RP	P.Y.183	300	7	5	5	5	5	5		△	△
	Permanent Yellow 2RP	P.Y.191:1	300	8	5	5	5	5	5			△
	Permanent Yellow RL	P.Y.192	300	8	5	5	5	5	5	△	△	△
	Permanent Yellow FG	P.Y.194	240	4-5	5	5	5	5	5			
Red	Pigment Red 123	P.R.123	250	7	5	5	5	5	5		△	△
	Permanent Red B	P.R.149	300	8	5	5	5	5	5		△	△
	Peramnent Red HFT	P.R.175	250	8	5	5	5	5	5	△	△	△
	Permanent Red HF3C	P.R.176	250	8	5	5	5	5	5	△	△	
	Permanent Red 3BL	P.R.177	250	8	5	5	5	5	5	△	△	△
	Permanent Red F4R	P.R.179	300	8	5	5	5	5	5		△	△
	Permanent Red HF2B	P.R.185	250	8	5	5	5	5	5		△	△
	Permanent Red F3S	P.R.188	200	7	4	5	5	5		△	△	
	Pigment Red 202	P.R.202	300	8	5	5	5	5	5	△	△	△
	Permanent Red S2B	P.R.208	250	8	5	5	5	5	5	△	△	△
	Permanent Red 4F	P.R.242	280	7	5	5	5	5	5	△	△	
	Pigment Red 254	P.R.254	300	8	5	5	5	5	5		△	△
	Pigment Red 255	P.R.255	300	8	5	5	5	5			△	
	Pigment Red 272	P.R.272	300	8	5	5	5	5	5		△	△
	Quindo Pink E	P.R.122	250	8	5	5	5	5	5	●	●	●
Orange	Permanent Orange HL	P.O.36	250	8	5	5	5	5	5	△	△	
	Pigment Orange 64	P.O.64	250	8	5	5	5	5	5	△	△	△
	Permanent Orange RN	P.O.71	300	8	5	5	5	5	5		△	△
	Permanent Orange G	P.O.73	300	8	5	5	5	5	5		△	△

High Performance Organic Pigment

Color	Item	C. I.No.	Physical and Chemical Property							Applications		
			Heat Resistance℃	Light Fastness	Acid Resistance	Alkali Resistance	Water Resistance	Oil Resistance	Immigration	Ink	Paint	Plastic
Violet	Quindo Violet 4R	P.V.19	250	8	5	5	5	5		△	△	△
	Permanent Violet RL	P.V.23	250	8	5	5	5	5		△	△	△
Blue	Pigment Blue 60	P.B.60	300	8	5	5	5	5	5	△	△	△
Brown	Pigment Brown HFR	P.BR.25	200	8	5	5	5	5	5			△

△:recommended ● can be sued

SINOPIGMENT
All for your
colorful life!

